



Texdecor - Casamance
2, rue d'Hem
59780 WILLEMS
France

Your notice of
 30-03-2021

Your reference

Date
 06-05-2021

Analysis Report 21.01998.54

Required tests :

California Technical Bulletin 117 (2013)

Sample id	Information given by the client	Date of receipt
T2107143	4850	30-03-2021



Gina Créelle
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2107143 - 4850

Section 1 : cover fabric test

Date of ending the test 03-05-2021
Standard used ASTM E1353-08a (2013)
Product standard California Technical Bulletin 117 (2013)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Filling T 30130 (Recticel) - non-fire retardant foam
Cover Sheetting Material Composition 100 % cotton - laundered weight (125 ± 28) g/m²

	1	2	3
Open flaming	no	no	no
Smoulders more than 45 min.	no	no	no
Vertical char length > 45 mm	no	no	no

Test criteria

- no open flaming
- smouldering ≤ 45 minutes
- vertical char ≤ 45 mm

Requirements

- all specimens meet the test criteria → PASS
- two or more specimens fail the test criteria → FAIL
- one specimen fails the test criteria → 3 additional tests → PASS
- all specimens meet the test criteria

Conclusion

Pass