



**Texdecor - Casamance**  
**2, rue d'Hem**  
**59780 WILLEMS**  
**France**

**Your notice of**  
22-06-2023

**Your reference**

**Date**  
08-08-2023

## Analysis Report 23.03469.08


**Required tests :**  
**NFPA 701 (2019)**

**Standard Methods of Fire Tests for Flame Propagation of  
Textiles and Films**

Sample id	Information given by the client	Date of receipt
T2314809	4019	22-06-2023

**Gina Créelle**  
**Order responsible**

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference:** T2314809 - 4019

**Standard Methods of Fire Tests for Flame Propagation of Textiles and Films**

Date of ending the test 28-06-2023  
Standard used NFPA 701 (2019)

Deviation from the standard -

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

The test specimens are dried in an oven for at least 30 min. at  $(105 \pm 3) ^\circ\text{C}$ .

Specimens are tested according to NFPA 701 – Test Method 1

Weight ( $\text{g}/\text{m}^2$ ) 123

Flame application time (s) 45

Length

	Afterflame time (s)	Flame time (s) droplets/ debris	Mass (g) before	Mass (g) after	Mass loss (%)
#1	0	0	7.7	5.3	31
#2	0	0	7.7	6.6	14
#3	0	0	7.7	6.2	19
#4	0	0	7.7	5.6	27
#5	0	0	7.6	6.2	18
#6	0	0	7.6	6.3	17
#7	0	0	7.6	6.4	16
#8	0	0	7.7	6.3	18
#9	0	0	7.8	6.3	19
#10	0	0	7.8	5.4	31
<b>Average</b>		<b>0</b>			<b>21</b>

<b>Standard deviation mass loss (<math>\sigma</math>)</b>	6
<b>Average + <math>3\sigma</math></b>	39

**Performance criteria**

- afterflame time debris (average) : not more than 2s
- mass loss (average) : not more than 40%
- mass loss (individual) : deviation not more than 3 standard deviations from the average

**Conclusion** **Pass**